

G-Energy Grease L EP 2

High Performance Multipurpose Extreme Pressure Lithium Grease

G-Energy Grease L EP 2 is multipurpose, extreme pressure grease based on a blend of high viscosity index mineral oils and a lithium hydroxystearate soap thickener and contains extreme pressure and other additives. G-Energy Grease L EP 2 is suitable for wide range of heavy duty plain and rolling bearings found in both automotive and general industrial applications. It provides excellent protection against rust, corrosion and wear under heavy loading and vibration. G-Energy Grease L EP 2 is recommended for use over the temperature range -30°C to 120°C.

Applications

G-Energy Grease L EP 2 is recommended to lubricate wheel bearings, generators and electric motors, joints, clutch pressure bearings, braking cylinders, ventilation systems, chassis parts, universal joints and water pumps on passenger cars, light trucks and other mobile equipment

| Features | Advantages and Potential Benefits | |
|--|---|--|
| Outstanding load carrying capacity | Reduced wear under heavy or shock loading and vibration for good equipment reliability and availability | |
| Excellent mechanical stability | Resistance to grease softening with subsequent loss of lubrication performance and leakage | |
| Excellent water and corrosion resistance | Extended bearing life in wet environments for reduced bearing costs and unexpected downtime | |
| Multipurpose grease | Wide variety of applications. One product for general lubrication of diverse mechanical equipment | |
| Wear protection | Excellent performance in both low and high temperature service for long engine life | |

Meets the requirements:

| Specification | G-Energy Grease L EP 2 | |
|---------------|------------------------|--|
| DIN 51502 | KP2K-30 | |

Typical Characteristics

| Properties | Method | G-Energy Grease L EP 2 |
|--|------------|------------------------|
| NLGI Grade | | 2 |
| Thickener Type | | Lithium |
| Color | visual | Brown |
| Penetration, worked 60 stokes, mm/10 | ASTM D217 | 265-295 |
| Dropping Point, °C | ASTM D566 | >190 |
| Base Oil Viscosity @40°C, mm ² /s | ASTM D445 | 150 |
| 4-Ball Wear Scar Diameter, mm | ASTM D2266 | 0,5 |
| 4-Ball Weld Load, N | ASTM D2596 | 2400 |
| Rust Protection, distilled water | ASTM D6138 | pass |
| Water Washout, wt% | ASTM D1264 | 10 |

Health, Safety & Environment

Information is provided for products in the relevant Safety Data Sheet (SDS). This provides guidance on potential hazards, precautions and first-aid measures, together with environmental effects and disposal of used products. SDS's are available upon request through your sales contract office. This product should not be used for purposes other than its intended use.